

⊕⊝*sunbattery*®

SB12-45(12V45AH)(SB12-45V0)

Specification

Nominal Voltage

Nominal Capacity (20HR)

Dimension

Approx Weight Terminal

Container Material

Rated Capacity

Max. Discharge Current
Internal Resistance

Operating Temp.Range

Nominal Operating Temp. Range

Cycle Use

Standby Use

Capacity affected by Temperature

Self Discharge

Life expectancy

12V

45.0AH

Length 197 ± 2 mm (7.76 inches)Width 165 ± 2 mm (6.50 inches)Container Height 170 ± 2 mm (6.69 inches)Total Height (with Terminal) 170 ± 2 mm (6.69 inches)

Approx 14.5 Kg(32.0 lbs)

T6

ABS Standard ABS UL94 HB Optional ABS UL94 V0

 45.0 AH/2.25A
 (20hr ,1.80V/ceII,25°C/77°F)

 42.0 AH/4.20A
 (10hr,1.80V/ceII,25°C/77°F)

 36.6 AH/7.31A
 (5hr,1.75V/ceII,25°C/77°F)

 32.7 AH/10.9A
 (3hr,1.75V/ceII,25°C/77°F)

 26.0 AH/26.0A
 (1hr,1.60V/ceII,25°C/77°F)

540A (5s)

Approx $9.0 m\Omega$

Discharge : $-15\sim50^{\circ}\text{C}$ (5 $\sim122^{\circ}\text{F}$) Charge : $0\sim40^{\circ}\text{C}$ (32 $\sim104^{\circ}\text{F}$) Storage : $-15\sim40^{\circ}\text{C}$ (5 $\sim104^{\circ}\text{F}$)

25±3°C (77±5°F)

Initial Charging Current less than 13.5A. Voltage 14.4V~15.0V at 25°C(77°F)Temp. Coefficient -30mV/°C

No limit on Initial Charging Current Voltage 13.5V~13.8V at 25°C(77°F)Temp. Coefficient -20mV/°C

 40°C
 (104°F)
 103%

 25°C
 (77°F)
 100%

 0°C
 (32°F)
 86%


SB series batteries may be stored for up to 6 months at 25° C(77° F) and then a freshening charge is required. For higher temperatures the time interval will be shorter.

8-12 years at 25°C with charge voltage 2.25V/cell.



Applications

- UPS and EPS
- ◆ Emergency light
- Railway signal and aircraft signal system
- Marine and power stations
 Alarm and security system
- Electronic apparatus and equipment
- Communication power supply, DC power supply




Comform to: IEC60896-21&22 and/or IEC61427


Constant Current Discharge (Amperes) at 25 (77°F) F.V/Time 10min 15min 20min 30 min 45min 1h 2h 3h 4h 5h 6h 10h 20h 8h 1.85V/cell 49 1 413 36.7 30.4 23.5 20.1 13.0 9 77 8.01 6 74 5.90 4.73 4 07 2.17 46.4 25.3 7.14 6.25 4.98 1.80V/cell 56.2 40.5 33.0 21.2 14.0 10.5 8.51 4.20 2.25 14.5 52.3 35.9 8.80 6.45 5.15 2.30 1.75V/cell 63.9 44.8 27.6 23.1 10.9 7.31 4.31 1.70V/cell 72.1 58.0 49.5 39.2 29.7 24.4 15.3 11.5 9.20 7.73 6.76 5.37 4.48 2.36 1.65V/cell 77.5 62.1 52.6 41.4 31.5 25.3 15.9 12.0 9.56 7.97 6.99 5.55 4.60 2.44 85.2 32.7 26.0 16.3 8.17 7.14 4.70 1.60V/cell 68.1 57.1 44.1 12.3 9.77 5.64 2.48


Constant Power Discharge (Watts/cell) at 25 °C (77°F)														
F.V/Time	10min	15min	20min	30min	45min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	91.8	77.9	69.8	58.6	45.6	39.1	25.5	19.2	15.8	13.3	11.7	9.44	8.14	4.34
1.80V/cell	103.8	86.4	76.1	62.6	48.8	41.1	27.2	20.6	16.7	14.1	12.4	9.91	8.38	4.49
1.75V/cell	116.0	96.2	83.3	67.5	52.7	44.6	28.2	21.3	17.2	14.4	12.7	10.2	8.60	4.60
1.70V/cell	128.1	105.2	91.3	73.3	56.6	47.0	29.7	22.4	18.0	15.2	13.3	10.6	8.92	4.71
1.65V/cell	136.3	111.8	96.4	76.7	59.3	48.3	30.6	23.2	18.6	15.6	13.7	11.0	9.16	4.85
1.60V/cell	146.5	120.4	103.6	81.3	61.3	49.5	31.2	23.7	19.0	15.9	14.0	11.1	9.33	4.92

Dimensions

T6 Terminal












Discharge Characteristics




Float Charging Characteristics




Temperature Effects in Relation to Battery Capacity



Effect of Temperature on Long Term Float Life





Self Discharge Characteristics

No supplementary charge required
(Carry out supplementary charge before use if 100% capacity is required.)

Supplementary charge required before use. Optional charging way as below:

B 1.Charged for above 3 days at limted current 0.25CA and constant volatge 2.25V/cell.

 $2. Charged \ for \ above \ 20 hours \ at \ limted \ current \ 0.25 CA \ and \ constant \ volatge \ 2.45 V/cell.$

3. Charged for 8~10 hours at limted current 0.05 CA .

Supplementary charge may often fail to recover the capacity.

The battery should never be left standing till this is reached.